

Material Data Sheet Aluminum Alloys

850

Chemical Composition
(% max, unless shown as range or min.)

	Al	Sn	Ti	Zn	Ni	Cr	Mn	Mg	Cu	Fe	Si
Minimum		5.50			.70				.70		
Maximum	Balance	7.00	.20		1.30		.10	.10	1.30	.70	.70

852

Chemical Composition
(% max, unless shown as range or min.)

	Al	Sn	Ti	Zn	Ni	Cr	Mg	Mn	Cu	Fe	Si
Minimum		5.50			.90		.60		1.70		
Maximum	Balance	7.00	.20		1.50		.90	.10	2.30	.70	.40

443

Chemical Composition
(% max, unless shown as range or min.)

	Al	Sn	Ti	Zn	Ni	Cr	Mn	Mg	Cu	Fe	Si
Minimum											4.50
Maximum	Balance		.25	.50		.25	.05	.50	.60	.80	6.00

850 Physical Properties

T5 Temper

Ultimate Tensile (ksi)	16.0
Yield (ksi in 0.2% Offset)	-
% Elongation in 2 inches	5.0
Typical BHN Hardness	30—60

852 Physical Properties

T5 Temper

Ultimate Tensile (ksi)	24.0
Yield (ksi in 0.2% Offset)	18
% Elongation in 2 inches	-
Typical BHN Hardness	45—75

443 Physical Properties

T5 Temper

Ultimate Tensile (ksi)	17.0
Yield (ksi in 0.2% Offset)	8
% Elongation in 2 inches	3.0
Typical BHN Hardness	25—55

6300 West Ridge Road, Erie, PA 16506

Phone: 814-838-8602 • Fax: 814-838-8917 • Sales@ErieBronze.com